Polyset

Filtration Adhesives for **PERFORMANCE**

PC-3210 Rigid White Urethane Filter Adhesive for FDA or Oil & Gas Applications

PC-3210 is a two-component, room-temperature cured, rigid polyurethane adhesive/molding compound designed for FDA and oil & gas filters. **PC-3210** is formulated with raw materials that are compliant with 21CFR§176.170, 21CFR§177.1680, &/or 21CFR§177.2600, thereby making the product suitable for dry food contact applications. The product's combination of low viscosity and quick gelling characteristics yields fast turnover time for efficient manufacturing throughput.

Key Features

- Low Mixed Viscosity with Ample Working Time
- Fast Gel Time Combined with a Low-Stress Cure
- Very Good Hydrolytic and Thermal Stability
- Broad Chemical Resistance with Excellent Resistance to Chlorine and other Harsh Chemicals

Typical Uncured Properties

Color

PC-3210 Resin (Polyol Component)	White	
PC-3210 Hardener (Isocyanate Component)	Dark Amber	
PC-3210 Mixed	White	
Viscosity (Brookfield) @ 25°C ± 1°C (77°F ± 2°F); cPs		
PC-3210 Resin	4000	
PC-3210 Hardener	200	
Density @ 25°C ± 1°C (77°F ± 2°F); Lbs./Gal. (g/cm3)		
PC-3210 Resin	12.15 (1.46)	
PC-3210 Hardener	10.30 (1.23)	
PC-3210 Mixed	11.49 (1.38)	

Mixing Specifications & Characteristics

Mix Ratio

Parts by Weight	100 parts Resin : 46.5 parts	Hardener
Parts by Volume	1.82 parts Resin : 1.0 part	Hardener
Processing Time @ 25°0	C ± 1°C (77°F ± 2°F); min:sec	
Gel Time (100 gram	mass; 250 mL beaker)	1:45
Full Cure		7 Days

Technical Bulletin Rev. Date: 5/18/2016



Typical Cured Properties

Color	White
Hardness; Shore D	78
Tensile Strength; psi	5165

Processing Instructions

For good results, automatic mixing and dispensing equipment should be used. Please consult with Polyset technical staff before making final processing decisions.

Storage Information

Keep away from flames. Material should be used once container is opened. Long term storage of opened material should be under nitrogen. Shelf life of both PC-3210 Resin and PC-3210 Hardener is 6 months (@ 25°C (77°F) in unopened containers.

Safety Information

Avoid direct contact. Use safety goggles or safety glasses with side shields and impervious gloves when handling PC-3210 Resin and PC-3210 Hardener. Refer to product Safety Data Sheets for complete health and safety information.

Limited Warranty: Polyset Company Inc. makes no warranty, expressed or implied, including any warranty of merchantability of fitness for a particular purpose. The sole remedy of Purchaser for any claim concerning this product, including, but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the discretion of Polyset Company Inc. Any claims concerning this product shall be submitted in writing within one year of the delivery date of this product to Purchaser and any claims not presented within that period are waived by Purchaser. IN NO EVENT SHALL POLYSET COMPANY INC. BE LIABLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDES LOSS OF PROFITS) OR PUNITIVE DAMAGES.