

PC-3141 Urethane Casting System

Tan Pool/Spa Urethane with Shore D 80 Hardness

Technical Bulletin

Rev. Date: 06/12/2014

PC-3141 is a two component, room temperature cured, filled, tough elastomeric urethane system designed for casting end caps for water filtration. The combination of low viscosity and unique gelling characteristics of the material make it ideal for filter manufacturing. The chemical composition has a high degree of hydrolysis resistance and has very little hardness loss in water at elevated temperatures (85°C). In addition, raw material composition will pass NSF requirements.

Key Features

- Low viscosity
- Tough
- Very good thermal stability
- Excellent water resistance
- Can be used for NSF Applications

Typical Uncured Properties

Color	
Resin	Off-white
Hardener	Dk. Amber
Mixed	Tan
Viscosity (Brookfield) @ 25°C ± 1°C (77°F ± 2°F); cPs	
Resin (Brookfield Spindle #6)	
@ 10 RPM	8900–9900
@ 50 RPM	4450–5450
Hardener	150–250
Density @ 25°C ± 1°C (77°F ± 2°F); Lbs./Gal. (g/cm ³)	
Resin	11.65–11.85 (1.41)
Hardener	10.20–10.40 (1.22)
Mixed	11.22–11.42 (1.35)

Mixing Specifications & Characteristics

Mix Ratio:	
Parts by Weight	100 parts Resin to 42.3 parts Hardener
Parts by Volume	2.0 parts Resin to 1.0 part Hardener
Processing Times @ 25°C ± 1°C (77°F ± 2°F); min:sec	
Gel Time (142 grams; 250 mL Beaker)	15:00 – 17:00
Full Cure Cycle	7 Days

Limited Warranty: Polyset Company Inc. makes no warranty, expressed or implied, including any warranty of merchantability of fitness for a particular purpose. The sole remedy of Purchaser for any claim concerning this product, including, but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the discretion of Polyset Company Inc. Any claims concerning this product shall be submitted in writing within one year of the delivery date of this product to Purchaser and any claims not presented within that period are waived by Purchaser. IN NO EVENT SHALL POLYSET COMPANY INC. BE LIABLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDES LOSS OF PROFITS) OR PUNITIVE DAMAGES.

Chemical Resistance: 168 Hours	% Hardness Change	% Weight Change
Dextron 6 @350°F (177°C)	3.4	-2.5
Transyn D @350°F (177°C)	3.4	-2.5

Typical Cured Properties

Color	Tan to Yellowish-brown
Hardness; Shore D	75–85

Processing Instructions

For good results, automatic mixing and dispensing equipment should be used. Please consult with Polyset technical staff before making final processing decisions.

Storage

Keep away from flames. Material should be used once container is opened. Long term storage of opened material should be under nitrogen. Shelf life of both resin and hardener is 6 months @ 25°C (77°F) in unopened containers. Storage temperatures for the hardener (isocyanate) should be maintained from 18–35°C. Under these storage conditions the hardener will remain clear for periods of up to six months.

If solidification should occur because of exposure to temperatures below 18°C, the product can be reheated up to 60°C in a well ventilated oven for the minimum amount of time necessary to render it clear. Excessive heating causes dimerization, loss of NCO, and increase in viscosity. In the event of crystallization, please contact Polyset for recommendations.

Safety Information

Avoid direct contact. Use gloves when handling resin and hardener, if skin contact occurs, wash with soap and water. If resin or hardener enters the eyes, flush with cool water for at least 15 minutes and call a physician immediately. Refer to PC-3141 Safety Data Sheets for further details.