

Ply-Guard AS

Ply-Guard AS is a fast-curing, two-component polyaspartic (aliphatic polyurea) coating system. Ply-Guard AS exhibits superior color and gloss retention, excellent abrasion resistance, and can be applied by sprayer or rollers directly to properly prepared concrete or metal surfaces. In addition, Ply-Guard AS has very good corrosion, chemical, and UV resistance, and can achieve a uniform coating thickness of 4-8 mils DFT per coat that is free of bubbles and pinholes.

Key Features

- Fast-curing (60 minutes @ 77°F / 25°C)
- Low-temperature cure (as low as 0°F / -34°C)
- 0 VOC (with exempt solvent)
- Recoat time: 90 Mins
- Walk-on Time: 2—3 Hours
- Self-priming, excellent penetration and bond strength
- Excellent abrasion, impact, and wear resistance
- Excellent color and gloss retention
- UV-resistant; optical clarity of clear sealer/finish
- Can add micro media agents to improve slip reduction
- Excellent resistance to chemicals and stains
- Skydrol resistant
- Random/incidental heat contact: tolerant to 300°F
- Available in gloss finish

Uses

Concrete Surfaces

- Commercial/Industrial Flooring - Two-coat system consisting of self-priming color primer/sealer or “bed” coat for accepting and wetting decorative flake chips (or other decorative media), followed by clear sealer/finish coat
- Final clear sealer/finish over decorative concrete surfaces such as acid, color or dye stained, semi-polished concrete, polymer-modified cementitious overlays, or seamless multi-build epoxy/color quartz flooring
- High foot traffic and vehicle/material-handling equipment areas
- UV-resistant sealer/finish coat over safety surfacing systems, outdoor running tracks, swimming pools, and patios

Steel surfaces

- Storage tanks
- Bridges
- Marine (ships, offshore rigs, barges, etc.)
- Railcars
- Pipelines

Limited Warranty: Polyset Company Inc. makes no warranty, expressed or implied, including any warranty of merchantability or fitness for a particular purpose. The sole remedy of Purchaser for any claim concerning this product, including, but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the discretion of Polyset Company Inc. Any claims concerning this product shall be submitted in writing within one year of the delivery date of this product to Purchaser and any claims not presented within that period are waived by Purchaser. IN NO EVENT SHALL POLYSET COMPANY INC. BE LIABLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDES LOSS OF PROFITS) OR PUNITIVE DAMAGES. Copyright © 2023 Polyset Company, Inc. All rights reserved. Revised 3/24/2023

Technical Bulletin

Surface Preparation

Concrete: Recommended surface profile is SP-2, Reference ICRI Technical Guideline No. 03732. This is best achieved with mechanical grinding machines using diamond heads achieving a final 50 to 120-grit profile.

Direct-To-Metal: All steel surfaces should be prepared to SSPC-SP10, Near-White finish with a minimum of 1.0 mil profile.

Mix Ratio

Parts by Volume: 1.0 part Base : 1.0 part Catalyst

Product Data (All readings taken at 77°F / 25°C, unless noted)

VOC Content (Lbs./gal.): 0

VOC Content (grams/Liter): 0

Flash Point: 39°F (4°C)

Type of Material: Polyaspartic (Aliphatic Polyurea)

Color: Clear with Standard Color Packs

Finish: Gloss

Volume Solids (%): 72

Theoretical Estimated Coverage (ft²/gal.):

1155 @ 1 mil DFT

Recommended Film Thickness (mils/coat):

4—8 mils DFT

Method of Application: Spray, Brush, or Roll

Thinner & Clean-Up Solvent: Xylene or MEK

Pot Life: Approximately 30 minutes @ 77°F / 25°C

Drying Time 60 minutes @ 77°F / 25°C & 50% RH

Increased film thickness will take longer. Do not exceed 48 hours between coats.

Shelf Life: 1 year in the original, unopened containers

Storage: Store between 40—95°F

Store in a dry, covered area away from direct sunlight

**FOR ADDITIONAL APPLICATION & EQUIPMENT RECOMMENDATIONS,
PLEASE CONSULT YOUR POLYSET TECHNICAL REPRESENTATIVE.**