



Ply-Seal® XE

Ply-Seal® XE is a pre-formed, low-density, closed-cell, cross-linked, nitrogen blown, Ethylene Vinyl Acetate (EVA), polyethylene copolymer material. Ply-Seal® XE is used as a flexible joint seal that is waterproof and chemical resistant. Ply-Seal® XE is compatible with construction materials and resistant to abrasion, oxidation, oils, gasoline, de-icing, salt, and other materials that may come in contact with the surface. Its standard color is gray and it conforms to ASTM D1056, Type 2 Class B, Grade 2.

Key Features

- Intersections and splices; field-welded quick and easy
- Weather and UV resistant—UV Inhibitor added
- Handles 30% tension and 60% compression
- Handles 100% vertical and horizontal shear
- A monolithic waterproof system
- Solvent and chemical resistance
- Not affected by extreme cold
- Hydrostatic Resistant to 70'
- Bonds to most substrates

Uses

Waterproof expansion/contraction joint seal ideal for bridges, car parks, tunnels, waste water treatment plants, and interior/exterior commercial structures.

Enhanced Bond Line Design

Ply-Seal® XE seals are manufactured with grooves along the bond surface running the length of the joint. The grooves are approximately 1/8" wide by 1/8" deep, and spaced between 1/4 and 1/2 inch apart. Splicing of the seal is performed using the heat-welding method.

Installation

Ply-Seal® XE is installed with Ply-Bonder, a 2-part epoxy on both sides of the substrate and both sides of the Ply-Seal® XE. The seal is installed under compression (see design chart). Please refer to the Joint Seal Installation Instructions for proper installation procedures.

Packaging: Fabricated per project requirements

Shelf Life: Unlimited

Storage: Maximum storage temperature: 95°F

Technical Bulletin

Physical Data

Property	Value	ASTM D3575
Density (Nominal)	3.0 pcf ± 0.3	Suffix W
Compressive Strength	6 psi @ 25% 15 psi @ 50%	Suffix D
Elongation	255% ± 10%	Suffix T
Tensile Strength	120 psi ± 12 psi	Suffix T
Tear Strength	17 pli ± 3 pli	Suffix G
Compression Set 22 Hrs. @ 50%	9% @ 24 Hrs. Rcvy (13% @ 2 Hrs. Rcvy)	Suffix B
Water Absorption	< 0.03 lb/ft ² 3% Vol/Vol Max	Suffix L
Weathering (AASHTO T42)	No Deterioration within 10 Years	

Model Number	Jt. Gap (in.) @ 60°F	Rec.* Seal Size (w x d)	Movement Range (in.)
#1.38	1	1 3/8 x 2	0.5 - 1.8
#1.63	1 1/4	1 5/8 x 2	0.6 - 2.1
#2.00	1 1/2	2 x 2	0.8 - 2.6
#2.38	1 3/4	2 3/8 x 2	0.9 - 3.1
#2.75	2	2 3/4 x 2	1.1 - 3.6
#3.00	2 1/4	3 x 2 1/2	1.2 - 3.9
#3.25	2 1/2	3 1/4 x 2 1/2	1.3 - 4.2
#3.50	2 3/4	3 1/2 x 2 1/2	1.4 - 4.5
#4.00	3	4 x 3	1.6 - 5.2
#4.50	3 1/2	4 1/2 x 3	1.8 - 5.8
#5.00	4	5 x 3 1/2	2.0 - 6.5

Limited Warranty: Polyset Company Inc. makes no warranty, expressed or implied, including any warranty of merchantability of fitness for a particular purpose. The sole remedy of Purchaser for any claim concerning this product, including, but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the discretion of Polyset Company Inc. Any claims concerning this product shall be submitted in writing within one year of the delivery date of this product to Purchaser and any claims not presented within that period are waived by Purchaser. IN NO EVENT SHALL POLYSET COMPANY INC. BE LIABLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDES LOSS OF PROFITS) OR PUNITIVE DAMAGES. Copyright © 2016 Polyset Company, Inc. All rights reserved. Revised 8/16.