

### PROTECTIVE COATINGS FOR PERFORMANCE



# WB HRZS® Single Coat System

WB HRZS® Single Coat System is a state-of-the-art, 100% WaterBorne High Ratio Zinc Silicate designed to protect steel structures. Originally developed by NASA to protect launch gantries from highly corrosive coastal ocean environments, WB HRZS® Single Coat System has been utilized successfully on many steel structures in Marine, Hydro, Military, and many other industries where high performance products are required.

#### **Key Features**

- 100% WaterBorne High Ratio Zinc Silicate (Inorganic)
- Excellent adhesion to steel (chemical bond), will not undercut
- Provides both galvanic and cathodic corrosion protection
- Single coat system, no topcoat required
- Self-curing (air dry)
- Passes hot seawater erosion test (MIL-P-23236)
- 10,000+ hour successful salt fog testing (ASTM B117)
- High temperature resistance (750°F)
- UV resistant
- NACE TM0304 approved
- High abrasion resistance
- Hard-fouling resistance to zebra mussels, barnacles, etc.
- 0 VOC

#### Uses

- Marine (ships, offshore rigs, dry-docks, barges)
- Railcars and Shipping Containers
- Hydro (gates, trash racks, turbines, etc)
- Storage Tanks
- Bridges
- Pipelines (buried or above ground)

#### **Surface Preparation**

All steel surfaces should be prepared to SSPC-SP10, Near-White Metal with a minimum of 1.0 mil profile.

#### Mixing

While mixing, add Part B (Metallic Zinc Powder) to Part A (Silicate) with constant stirring. **DO NOT ADD PART A TO PART B.** After mixing, pour the product through a 40-mesh screen into a pressure pot or second pail. Continually agitate while applying the mixed product.

## **Technical Bulletin**

**Product Specifications:** 

Part A: Liquid Silicate Binder
Viscosity (cPs); ASTM D2196: 20—40
Appearance: Clear Liquid
Part B: Fine Metallic Zinc Powder
(ASTM D520)

Mix Ratio:

Parts by Weight: 1.00 Part A: 2.55 Part B
Parts by Volume: 2.27 Part A: 1.00 Part B

**Mixed Properties:** 

recommendations.

Gray/Matte Color:  $120 \pm 20$ Viscosity (cPs):  $25.0 \pm 0.2$ Density (Lbs./Gal.): Density (kg/L):  $3.00 \pm 0.1$  $80 \pm 2$ Solids in Mixed Solution (wt. %): Solids in Mixed Solution (vol. %):  $68 \pm 2$ Zinc in Dry Film (wt. %):  $91 \pm 2$ Zinc in Dry Film (vol. %):  $77 \pm 2$ **Estimated Coverage:** 1090 ft2 / Gal. @ 1.0 mil DFT

**Pot Life :** 6—8 Hrs @ 70°F **Recommended Dry Film Thickness**: 6-8 mils DFT

VOC Content: 0

Drying Time: 15—30 Minutes @ 77°F

**Application:** Automated or conventional spray. Contact your Polyset Technical Representative for equipment

Shelf Life: 2 years in the original, unopened containers Storage: Store between 60—95°F (16—35°C)

#### FOR PROFESSIONAL USE ONLY

Impervious gloves, protective clothing, and splash-resistant goggles are recommended. Direct contact with skin should be avoided as it may cause irritation. Harmful if ingested. Keep from open flames.

FOR ADDITIONAL APPLICATION INSTRUCTIONS AND EQUIPMENT, PLEASE CONSULT YOUR POLYSET TECHNICAL REPRESENTATIVE.

Limited Warranty: Polyset Company Inc. makes no warranty, expressed or implied, including any warranty of merchantability of fitness for a particular purpose. The sole remedy of Purchaser for any claim concerning this product, including, but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the discretion of Polyset Company Inc. Any claims concerning this product shall be submitted in writing within one year of the delivery date of this product to Purchaser and any claims not presented within that period are waived by Purchaser. IN NO EVENT SHALL POLYSET COMPANY INC. BE LIABLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDES LOSS OF PROFITS) OR PUNITIVE DAMAGES. Copyright © 2024 Polyset Company, Inc. All rights reserved. Revised 12/16/24





